

SPINNAKER YACHT VARNISH

data sheet



STANDARD

SPINNAKER Standard Yacht Varnish

It is an easy-to-use, very high quality, UV-resistant, high-performance single-component transparent varnish. Forms a very glossy film of superior durability, non-yellowing, resistant to atmospheric agents and saltiness.

Technical features

Guy: single component

Gloss: very bright

Color: transparent amber

Density: 0.92 Kg/dm³

Viscosity: 60 seconds ISO cup 6 mm

Dry residue: 50+/-2 %

Recommended thickness: 60-70 microns +/-2 %

Application temperature: between 8°C and 30°C (50-85°F). Humidity below 75%

Drying at 20°C: dust dry 3 hours - recoat in 24 hours.

Property

SPINNAKER Standard protects, maintains and enhances the very elastic grain of the wood.

Easy to apply both by brush and roller thanks to the excellent expansion.

Ideal for all external and internal woods even if of an oily type such as teak and iroko.

After waiting 24 hours, give the wood a light caress with paper 280 - 320 to remove any impurities (time to be used for 5m² – 2 minutes), wipe with a dust-proof cloth and apply the next coat. The light intermediate sanding leaves a surface with more body and allows you to have a track to apply the new coat.

Surface preparation and painting cycle

Make sure the surface is clean, dry and free from grease

New wood

- 1) Lightly sand with 220-240 paper in the direction of the grain of the wood
- 2) Apply the first coat diluted 20-30% with White Spirit so that it penetrates well wood grain.
- 3) Wait 24 hours
- 4) Sand with 320-360 paper to eliminate the "hair of the wood", dust with dust cloth.
- 5) Subsequent coats, one every 24 hours, can also be applied without dilution at most dilute by 5-10% depending on the temperature always with White Spirit.
- 6) 6 to 8 coats are recommended.

SPINNAKER YACHT VARNISH

data sheet



Painted wood brought back to new

- 1) Before painting, the homogeneity of the color must be checked, after stripping or after sanding the previous coats with 240-280 paper. It is advisable to abundantly wet all the woods with a sponge and lots of water or with a rag.
If the resulting shade is all uniform, fine, otherwise you have to sand again and then clean the wood with Nautilus Teak & Wood Cleaner which whitens and uniforms more. If parts with paint remain, even in depth, you risk the effect leopard spot.
- 2) Then follow the painting cycle as specified in the previous section from point 2.

Painted wood in good condition

- 1) Sand with 280-320 paper to make it easy to anchor the subsequent coats
- 2) Apply 2 to 3 coats, one every 24 hours, diluted by a maximum of 5-10% depending on temperature with White Spirit.

Technical and commercial data

packs: 1 lt. (12 pieces each carton);

Surrender: approx. 14 m²/lt

Diluent: White Spirit;

Application by brush or roller: good quality

Spray application: dilute 15-20%; 1.2-1.5mm nozzle; pressure 2-3 Bars.

Recommendations

Avoid applying with too much wind and under the sun

Do not apply wet on wet and do not apply too thickly